



MTB3500040

Type: Short twist drill

d1	d2	l1	l2
0,40	0,40	30	5,00

Coolant holes	Cut	Point angle	Spiral angle	Cutting edges Z
No	Right	118°	25°	2

Coated	Coating type	Material	Material type	Norm
No	-	MD	SMG 10	TUSA

Machinable Materials				
Cod.	Material type	Machinability	Cutting speed Vc	Advancement per revolution fn
		Recommended Part. recommended Not recommended	(m/min)	(mm/rev)
P01	Unalloyed steels up to 800 N/mm2		40 : 60	0,005 - 0,01
P02	Low alloy steels from 800 N/mm2 to 1100 N/mm2		30 : 50	0,005 - 0,01
P03	Highly alloyed steels from 1100 N/mm2 to 1400 N/mm2		-	-
M01	Ferritic stainless steels		15 : 30	0,003 - 0,008
M02	Martensitic stainless steels		15 : 30	0,003 - 0,008
M03	Martensitic stainless steels - PH		15 : 30	0,003 - 0,008
M04	Austenitic stainless steels		15 : 30	0,003 - 0,008
K01	Gray/lamellar cast iron		30 : 50	0,005 - 0,01
K02	Nodular/nodular cast iron		30 : 50	0,005 - 0,01
N01	Drawn aluminum alloys		60 : 100	0,005 - 0,015
N02	Die-cast aluminum alloys		50 : 80	0,005 - 0,015
N03	Copper		30 : 60	0,005 - 0,015
N04	Brass - Bronze		40 : 70	0,005 - 0,015
N05	Lead-free brass		30 : 60	0,005 - 0,015
S01	Super alloys (Inconel - Hastelloy - Nimonic)		-	-
S02	Pure titanium (Grade 2 - Grade 4)		30 : 50	0,002 - 0,007
S03	Titanium alloys (Grade 5)		30 : 50	0,002 - 0,007
S04	Cobalt Chrome Alloys		-	-
H01	Hardened steels up to 55 HRC		-	-

Machinable Materials

Cod.	Material type	Machinability	Cutting speed Vc	Advancement per revolution fn
		Recommended Part. recommended Not recommended	(m/min)	(mm/rev)
P01	Unalloyed steels up to 800 N/mm2		40 : 60	0,005 - 0,01
P02	Low alloy steels from 800 N/mm2 to 1100 N/mm2		30 : 50	0,005 - 0,01
P03	Highly alloyed steels from 1100 N/mm2 to 1400 N/mm2		-	-
M01	Ferritic stainless steels		15 : 30	0,003 - 0,008
M02	Martensitic stainless steels		15 : 30	0,003 - 0,008
M03	Martensitic stainless steels - PH		15 :30	0,003 - 0,008
M04	Austenitic stainless steels		15 : 30	0,003 - 0,008
K01	Gray/lamellar cast iron		30 : 50	0,005 - 0,01
K02	Nodular/nodular cast iron		30 : 50	0,005 - 0,01
N01	Drawn aluminum alloys		60 : 100	0,005 - 0,015
N02	Die-cast aluminum alloys		50 : 80	0,005 - 0,015
N03	Copper		30 : 60	0,005 - 0,015
N04	Brass - Bronze		40 : 70	0,005 - 0,015
N05	Lead-free brass		30 : 60	0,005 - 0,015
S01	Super alloys (Inconel - Hastelloy - Nimonic)		-	-
S02	Pure titanium (Grade 2 - Grade 4)		30 : 50	0,002 -0,007
S03	Titanium alloys (Grade 5)		30 : 50	0,002 -0,007
S04	Cobalt Chrome Alloys		-	-
H01	Hardened steels up to 55 HRC		-	-

H02	Hardened steels from 55 HRC		-	-
-----	-----------------------------	---	---	---



SWISS HIGH PRECISION TOOLS

