

TA80300125





















Type: Centesimal drill without coolant holes for steel

| d1 | d2 | l1 | l2 | l3 |
|------|------|----|-------|-------|
| 1,25 | 3,00 | 38 | 10,00 | 11,00 |

| Coolant holes | Cut | Point angle | Spiral angle | Cutting edges Z |
|---------------|-------|-------------|--------------|-----------------|
| No | Right | 130° | 35° | 2 |

| Coated | Coating type | Material | Material type | Norm |
|--------|--------------|----------|---------------|------|
| Yes | ALCRONOS | MD | SMG 10 | TUSA |

| Machinable Materials | | | | |
|----------------------|---|---|------------------|-------------------------------|
| Cod. | Material type | Machinability | Cutting speed Vc | Advancement per revolution fn |
| | | Recommended Part. recommended Not recommended | (m/min) | (mm/rev) |
| P01 | Unalloyed steels up to 800 N/mm2 |  | 35 : 65 | 0.014-0.025 |
| P02 | Low alloy steels from 800 N/mm2 to 1100 N/mm2 |  | 28 : 55 | 0.012-0.023 |
| P03 | Highly alloyed steels from 1100 N/mm2 to 1400 N/mm2 |  | 23 : 50 | 0.011-0.020 |
| M01 | Ferritic stainless steels |  | 28 : 55 | 0.010-0.018 |
| M02 | Martensitic stainless steels |  | 20 : 35 | 0.008-0.016 |
| M03 | Martensitic stainless steels - PH |  | 20 : 35 | 0.008-0.016 |
| M04 | Austenitic stainless steels |  | 20 : 35 | 0.008-0.016 |
| K01 | Gray/lamellar cast iron |  | 35 : 65 | 0.017-0.025 |
| K02 | Nodular/nodular cast iron |  | 30 : 55 | 0.012-0.022 |
| N01 | Drawn aluminum alloys |  | 45 : 80 | 0.012-0.020 |
| N02 | Die-cast aluminum alloys |  | 45 : 70 | 0.014-0.022 |
| N03 | Copper |  | 35 : 65 | 0.012-0.020 |
| N04 | Brass - Bronze |  | 35 : 65 | 0.009-0.016 |
| N05 | Lead-free brass |  | 40 : 70 | 0.012-0.020 |
| S01 | Super alloys (Inconel - Hastelloy - Nimonic) |  | 23 : 50 | 0.012-0.020 |
| S02 | Pure titanium (Grade 2 - Grade 4) |  | 18 : 35 | 0.006-0.011 |
| S03 | Titanium alloys (Grade 5) |  | 18 : 35 | 0.006-0.011 |
| S04 | Cobalt Chrome Alloys |  | 12 : 20 | 0.006-0.011 |
| H01 | Hardened steels up to 55 HRC |  | 12 : 20 | 0.006-0.011 |

| Machinable Materials | | | | |
|----------------------|---|---|------------------|-------------------------------|
| Cod. | Material type | Machinability | Cutting speed Vc | Advancement per revolution fn |
| | | Recommended Part. recommended Not recommended | (m/min) | (mm/rev) |
| P01 | Unalloyed steels up to 800 N/mm2 |  | 35 : 65 | 0.014-0.025 |
| P02 | Low alloy steels from 800 N/mm2 to 1100 N/mm2 |  | 28 : 55 | 0.012-0.023 |
| P03 | Highly alloyed steels from 1100 N/mm2 to 1400 N/mm2 |  | 23 : 50 | 0.011-0.020 |
| M01 | Ferritic stainless steels |  | 28 : 55 | 0.010-0.018 |
| M02 | Martensitic stainless steels |  | 20 : 35 | 0.008-0.016 |
| M03 | Martensitic stainless steels - PH |  | 20 : 35 | 0.008-0.016 |
| M04 | Austenitic stainless steels |  | 20 : 35 | 0.008-0.016 |
| K01 | Gray/lamellar cast iron |  | 35 : 65 | 0.017-0.025 |
| K02 | Nodular/nodular cast iron |  | 30 : 55 | 0.012-0.022 |
| N01 | Drawn aluminum alloys |  | 45 : 80 | 0.012-0.020 |
| N02 | Die-cast aluminum alloys |  | 45 : 70 | 0.014-0.022 |
| N03 | Copper |  | 35 : 65 | 0.012-0.020 |
| N04 | Brass - Bronze |  | 35 : 65 | 0.009-0.016 |
| N05 | Lead-free brass |  | 40 : 70 | 0.012-0.020 |
| S01 | Super alloys (Inconel - Hastelloy - Nimonic) |  | 23 : 50 | 0.012-0.020 |
| S02 | Pure titanium (Grade 2 - Grade 4) |  | 18 : 35 | 0.006-0.011 |
| S03 | Titanium alloys (Grade 5) |  | 18 : 35 | 0.006-0.011 |
| S04 | Cobalt Chrome Alloys |  | 12 : 20 | 0.006-0.011 |
| H01 | Hardened steels up to 55 HRC |  | 12 : 20 | 0.006-0.011 |
| H02 | Hardened steels from 55 HRC |  | - | - |