

TC35000115





















Type: Micro drill

d1	d2	l1	l2
1,15	1,15	38	16,00

Coolant holes	Cut	Point angle	Spiral angle	Cutting edges Z
No	Right	130°	35°	2

Coated	Coating type	Material	Material type	Norm
No	-	MD	SMG 10	TUSA

Machinable Materials				
Cod.	Material type	Machinability	Cutting speed Vc	Advancement per revolution fn
		Recommended Part. recommended Not recommended	(m/min)	(mm/rev)
P01	Unalloyed steels up to 800 N/mm2		40 : 60	0,006 - 0,02
P02	Low alloy steels from 800 N/mm2 to 1100 N/mm2		30 : 50	0,006 - 0,15
P03	Highly alloyed steels from 1100 N/mm2 to 1400 N/mm2		15 : 30	0,003 - 0,01
M01	Ferritic stainless steels		15 : 30	0,003 - 0,01
M02	Martensitic stainless steels		15 : 30	0,003 - 0,01
M03	Martensitic stainless steels - PH		15 : 30	0,003 - 0,01
M04	Austenitic stainless steels		15 : 30	0,003 - 0,01
K01	Gray/lamellar cast iron		30 : 50	0,01 - 0,02
K02	Nodular/nodular cast iron		30 : 50	0,01 - 0,02
N01	Drawn aluminum alloys		60 : 100	0,01 - 0,03
N02	Die-cast aluminum alloys		50 : 80	0,008 - 0,02
N03	Copper		30 : 60	0,008 - 0,03
N04	Brass - Bronze		40 : 70	0,008 - 0,03
N05	Lead-free brass		30 : 60	0,008 - 0,03
S01	Super alloys (Inconel - Hastelloy - Nimonic)		15 : 30	0,003 - 0,007
S02	Pure titanium (Grade 2 - Grade 4)		30 : 50	0,005 - 0,01
S03	Titanium alloys (Grade 5)		30 : 50	0,005 - 0,01
S04	Cobalt Chrome Alloys		15 : 30	0,003 - 0,007
H01	Hardened steels up to 55 HRC		-	-

Machinable Materials				
Cod.	Material type	Machinability	Cutting speed Vc	Advancement per revolution fn
		Recommended Part. recommended Not recommended	(m/min)	(mm/rev)
P01	Unalloyed steels up to 800 N/mm2		40 : 60	0,006 - 0,02
P02	Low alloy steels from 800 N/mm2 to 1100 N/mm2		30 : 50	0,006 - 0,15
P03	Highly alloyed steels from 1100 N/mm2 to 1400 N/mm2		15 : 30	0,003 - 0,01
M01	Ferritic stainless steels		15 : 30	0,003 - 0,01
M02	Martensitic stainless steels		15 : 30	0,003 - 0,01
M03	Martensitic stainless steels - PH		15 : 30	0,003 - 0,01
M04	Austenitic stainless steels		15 : 30	0,003 - 0,01
K01	Gray/lamellar cast iron		30 : 50	0,01 - 0,02
K02	Nodular/nodular cast iron		30 : 50	0,01 - 0,02
N01	Drawn aluminum alloys		60 : 100	0,01 - 0,03
N02	Die-cast aluminum alloys		50 : 80	0,008 - 0,02
N03	Copper		30 : 60	0,008 - 0,03
N04	Brass - Bronze		40 : 70	0,008 - 0,03
N05	Lead-free brass		30 : 60	0,008 - 0,03
S01	Super alloys (Inconel - Hastelloy - Nimonic)		15 : 30	0,003 - 0,007
S02	Pure titanium (Grade 2 - Grade 4)		30 : 50	0,005 - 0,01
S03	Titanium alloys (Grade 5)		30 : 50	0,005 - 0,01
S04	Cobalt Chrome Alloys		15 : 30	0,003 - 0,007
H01	Hardened steels up to 55 HRC		-	-
H02	Hardened steels from 55 HRC		-	-



SWISS HIGH PRECISION TOOLS
