



## TTD2060470E

**Type:** Punta elicoidale ad alte prestazioni con canalini corta

| d1   | d2   | l1   | l2    | l3    |
|------|------|------|-------|-------|
| 4,70 | 6,00 | 85,0 | 20,70 | 43,75 |

| Coolant holes | Cut   | Point angle | Spiral angle | Cutting edges Z |
|---------------|-------|-------------|--------------|-----------------|
| Yes           | Right | 130°        | -            | 2               |

| Coated | Coating type | Material | Material type | Norm |
|--------|--------------|----------|---------------|------|
| Yes    | ALCRONOS     | MD       | SMG 10        | TUSA |

| Machinable Materials |                                                     |                                                                                     |                  |                               |
|----------------------|-----------------------------------------------------|-------------------------------------------------------------------------------------|------------------|-------------------------------|
| Cod.                 | Material type                                       | Machinability                                                                       | Cutting speed Vc | Advancement per revolution fn |
|                      |                                                     | Recommended<br>Part.<br>recommended Not<br>recommended                              | (m/min)          | (mm/rev)                      |
| P01                  | Unalloyed steels up to 800 N/mm2                    |    | 50 : 80          | 0.20-0.22                     |
| P02                  | Low alloy steels from 800 N/mm2 to 1100 N/mm2       |    | 45 : 65          | 0.19-0.21                     |
| P03                  | Highly alloyed steels from 1100 N/mm2 to 1400 N/mm2 |    | 40 - 60          | 0.18-0.20                     |
| M01                  | Ferritic stainless steels                           |    | 35 - 50          | 0.13-0.14                     |
| M02                  | Martensitic stainless steels                        |    | 30 - 45          | 0.13-0.14                     |
| M03                  | Martensitic stainless steels - PH                   |    | 30 - 45          | 0.13-0.14                     |
| M04                  | Austenitic stainless steels                         |   | 30 - 45          | 0.12-0.13                     |
| K01                  | Gray/lamellar cast iron                             |  | 80 - 100         | 0.20-0.22                     |
| K02                  | Nodular/nodular cast iron                           |  | 80 - 100         | 0.20-0.22                     |
| N01                  | Drawn aluminum alloys                               |  | 100 : 160        | 0.155-0.16                    |
| N02                  | Die-cast aluminum alloys                            |  | 80 : 140         | 0.165-0.18                    |
| N03                  | Copper                                              |  | 60 : 100         | 0.145-0.16                    |
| N04                  | Brass - Bronze                                      |  | 80 : 140         | 0.17-0.185                    |
| N05                  | Lead-free brass                                     |  | 60 : 120         | 0.15-0.165                    |
| S01                  | Super alloys (Inconel - Hastelloy - Nimonic)        |  | 20 : 40          | -                             |
| S02                  | Pure titanium (Grade 2 - Grade 4)                   |  | 10 : 25          | 0.09-0.10                     |
| S03                  | Titanium alloys (Grade 5)                           |  | 15 - 30          | 0.11-0.12                     |
| S04                  | Cobalt Chrome Alloys                                |  | 35 - 50          | 0.11-0.12                     |
| H01                  | Hardened steels up to 55 HRC                        |  | 20 - 30          | 0.035-0.04                    |
| H02                  | Hardened steels from 55 HRC                         |  | -                | 0.035-0.04                    |